MagicEzy Hairline Fix

Tips & Secrets

Repairing fine stress cracks is now simple and 'EZY', plus the repairs are guaranteed for 3 years*.

HOW TO APPLY









1. PREPARE

- MagicEzy Hairline Fix is water resistant. It is not recommended for use on areas continually submerged in water.
- Scrape fine hairline cracks with a pin or use a toothbrush to remove trapped grime and dirt etc.
- Add a drop of dishwashing detergent in a cup of water and scrub into damage, then rinse with clean water.
- Allow to fully dry or use a hairdryer to accelerate drying time.
- Massage/rotate the tube between hands and then shake vigorously to ensure even consistency.

2. APPLY

- Have a tissue ready.
- Apply a few drops into the hairline crack.
- Do not apply too much as it may become messy.

3. LEVEL

- Turn the tube around and rapidly wipe across the repair several times with the patented 'LEVEL'. These wipes are important as they also help Hairline Fix penetrate deeply into the damage.
- Clean the end of the LEVEL with the tissue.
- Level again.
- Very deep cracks may require several coats to fill completely. Allow at least 2 hours in between coats before re-applying (overnight is best).

4. TRIM

Trim to remove smears outside the repair edge (but not the repair itself).
Use a damp cloth or tissue to help clean-up if necessary.

REPAIR SECRETS

How do I achieve a good color match?

Simply mix two or more colors to form a new color on a piece of transparent plastic wrap placed over the surface.

How do I apply on vertical surfaces?

To prevent slumping or for a faster dry time, use a hairdryer for 4 minutes to form a skin.

How do I use as a glossy top coat for 9 Second Chip Fix repairs?

Simply apply a thin layer over the cured 9 Second Chip Fix and gently LEVEL. (Sometimes levelling is not necessary)

How do I apply in hot / cold weather?

In temperatures below 70°F (20°C), warm the surface for a couple of minutes with a hot hair dryer. In temperatures above 90°F (30°C), Cool the surface by laying a damp towel over the area before applying.



Product shelf life before opening: 2 years.

Product life after opening: 6 months subject to storing below 50°F / 10°C .

Unit size: .45 floz/12.5ml tube.

Ingredients: Proprietary acrylic resins, Zinc Oxide (1314-13,2), Dipropylene Glycol (25265-71-8)

*We guarantee the repairs will last for 3 years if the product is applied in accordance with instructions OR your money back.

